

## FT-Card

## 5020 Fintex 20

<b>Product</b>	Semi-matt, washable, waterborne acrylate dispersion paint with excellent opacity
<b>Suitability</b>	Can be used as topcoat on walls and ceilings indoors. Suitable for concrete, plaster and filler surfaces along with various types of construction boards e.g. wood, chipboard, plywood, plasterboard, glass fibre wall coverings and paintable wallpapers. Usable for new and previously painted surfaces.
<b>Properties</b>	<p>excellent opacity</p> <p>solvent free</p> <p>A and C bases available, tintable with common tinting systems</p> <p>washable</p> <p>good rubbing resistance</p> <p>semi-matt finish</p> <p>produced in Finland</p> <p>mild odor</p> <p>fulfills requirements for best indoor air classification M1</p>

## Technical data

<b>Dry contents</b>	appr. 49 %	
<b>Density</b>	1,30 g/ml.	
<b>Grade of gloss</b>	RT4, (Finnish classification), semi-matt.	
<b>MT-group</b>	MT314, (Finnish classification).	
<b>Rubbing resistance</b>	Good, stands more than 15000 brush strokes, SFS3455. SFS-EN 13300 class I, ISO11998.	
<b>Tinting</b>	Tintable according to common colour cards.	
<b>Storage</b>	36 months in original package, to be stored in dry, cool surroundings, temperature between +5...+25°C.	
<b>Coverage</b>	Previously painted surfaces	8-12 m <sup>2</sup> /l
	Wood and construction boards	6-10 m <sup>2</sup> /l
	Concrete, plaster and filler surfaces	5-7 m <sup>2</sup> /l
	Fibre glass wall coverings and wallpapers	5-7 m <sup>2</sup> /l
<b>Drying time</b>	Painted surface is dust dry in 30 minutes, repaintable after 2 hours. Drying times are estimated and dependable on temperature, relative humidity of air and ventilation.	
<b>Tools</b>	Spray gun, brush or roller.	
<b>Thinning</b>	Water.	
<b>Cleaning of tools</b>	Water.	
<b>Package sizes</b>	0,9, 2,7, 9 and 18 litres.	
<b>Transportation</b>	Non ADR-classified. Must be kept from freezing.	
<b>Flammability</b>	Non-flammable	
<b>EU VOC limit</b>	cat.A/d 30g/l (2010), ready mixed product VOC max.30g/l.	

## FT-Card

### Instructions

**Circumstances** Temperature must be over +5°C but under +25°C relative humidity of air below 80 %.

**Instructions** Remove dirt and dust from the surface to be painted. When required wash surfaces with 5059 Maalarin Tehopesu. Fill holes and cracks with Fintex-filler or with 1200 Tetramassa before painting. Apply 1-2 layers as required for lacquered inner ceilings 2-4 layers. Paint can be applied with a brush, roller or spray gun. . As primer on walls it is recommended to use 5002 Fintex 2 or 5005 Fintex 5. When used for old wooden ceilings it is recommended to use 5008 Fintex Stoppari as primer to block resins and branch marks. Even after being most opaque there can still be some visual marks on painted surface within years. Always use proper protective clothing and protective device during paint work.

The information on this data sheet is based on laboratory tests and practical results. All test results are indicative. As we can not influence the working conditions and methods we are only responsible for the quality of the paint which is guaranteed in accordance with our high quality requirements. We are not liable for any damage caused by incorrect use of the product against instructions or if used for inappropriate purpose.

### Environmental protection

Liquid paint is to be handled as hazardous waste. Empty, dry cans can be recycled or dealt as standard household waste.

**Product safety** Contents of the product do not require any warning labels. A material safety data sheet is available.

**Flammability** Non flammable.